## LUCIDUS YELLOW 3G



Methine			C.I. Solvent Yellow 93 Colour Index No. 48160				
Technical	Application D	ata					
			PS	ABS	PC	PET	PA 6
Heat Stability(C°)			300	250	340	320	_
Light Fastness SD $\frac{1}{3}$ Full Shade			7-8	7	8	8	_
Light Fastness SD $\frac{1}{3}$ Reduction			7-8	7	7-8	8	-
Physical a	nd Chemical (	Characteristics					
Shade					Greenish yellow		
CAS No.					4702-90-3		
Density( g	/cm <sup>3</sup> )				1.38		
Melting po	pint(C°)				180		
Alkali resis	tance				5		
Acid resist	ance				5		
Range of A	Applications						
						Spin Dyeing	
PS	•	PC	•	PMMA	•	PET	_
SAN	•	PET	_	PA 6	_	PA	_
ABS	_	PBT	_	PA 66	_	PAN	_

## Commentary

Solvaperm Yellow 3G is a brilliant yellow with excellent light fastness and good heat resistance. Suitable for coloration of PS, SAN, PC, PMMA and PVC-R.

Note : Data Presented above is based on our present knowledge and is with intentions of providing general guidelines for use of our products. These products are offered by TINTEC without any kind of guarantee. We recommend that customers should test the suitability of these products in their end application before use.