

LUCIDUS YELLOW G

Quinophthalone

C.I. Solvent Yellow 114
Colour Index No. 47020



Technical Application Data

	PS	ABS	PC	PET	PA 6
Heat Stability(C°)	300	280	340	290	—
Light Fastness SD $\frac{1}{3}$ Full Shade	8	7	8	8	—
Light Fastness SD $\frac{1}{3}$ Reduction	7-8	7	7-8	7-8	—

Physical and Chemical Characteristics

Shade	Neutral yellow
CAS No.	84-65-1
Density(g/cm ³)	1.53
Melting point(C°)	264
Alkali resistance	5
Acid resistance	5

Range of Applications

						Spin Dyeing	
PS	●	PC	●	PMMA	●	PET	●
SAN	●	PET	●	PA 6	—	PA	—
ABS	●	PBT	●	PA 66	—	PAN	—

Commentary

Solvaperm Yellow EG is a brilliant yellow with excellent light fastness and good heat resistance. Suitable for coloration of PS, SAN, PC, PMMA and PVC-R.

Note : Data Presented above is based on our present knowledge and is with intentions of providing general guidelines for use of our products. These products are offered by TINTEC without any kind of guarantee. We recommend that customers should test the suitability of these products in their end application before use.